


Attorney's Docket: 2004DE105
 Serial No.: 10390828
 Art Unit: 1756
 Response to Office Action Mailed 08/16/2007

This listing of claims will replace all prior versions, and listings, of claims in the application:

- 1) (Currently Amended) A colorant for pigmenting an Inkjet-ink or a color filter comprising a pigment composition comprising between 86.0 and 99.9 overall mol% of C.I. Pigment Yellow 74 molecules and between 14.0 and 0.1 overall mol% of at least one monoazo pigment of the formula (1)



wherein R' is Cl, OCH₃, CH₃ or NO₂

wherein the pigment composition comprises more than 15% by weight, based on the overall weight of the pigment composition, of mixed crystals of C.I. Pigment Yellow 74 and the at least one monoazo pigment of formula (1) and wherein the mixed crystals contain between 70 and 99.9 mol% of Pigment Yellow 74 and between 30 and 0.1 mol% of the at least one monoazo pigment of formula (1).

- 2) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition comprises between 86.5 and 99.5 overall mol% of the C.I. Pigment Yellow 74 molecules and between 13.5 and 0.5 overall mol% of the at least one monoazo pigment of the formula (1).

Attorney's Docket: 2004DE105
Serial No.: 10590.828
Art. Unit: 17/55
Response to Office Action Mailed 08/16/2007

- 3) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition comprises between 87.0 and 94.0 overall mol% of the C.I. Pigment Yellow 74 molecules and between 13.0 and 6.0 overall mol% of the at least one monoazo pigment of the formula (1).
- 4) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition comprises between 88 and 92 overall mol% of the C.I. Pigment Yellow 74 molecules and between 12 and 8 overall mol% of C.I. Pigment Yellow 65 molecules.
- 5) (Canceled)
- 6) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition comprises more than 30% by weight, based on the overall weight of the pigment composition, of mixed crystals of the C.I. Pigment Yellow 74 and the at least one monoazo pigment of the formula (1).
- 7) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition comprises more than 50% by weight, based on the overall weight of the pigment composition, of mixed crystals of the C.I. Pigment Yellow 74 and the at least one monoazo pigment of the formula (1).

Attorney's Docket: 200405105
 Serial No.: 107590828
 Art Unit: 1765
 Response to Office Action Mailed 08/18/2007


8) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition comprises more than 75% by weight, based on the overall weight of the pigment composition, of mixed crystals of the C.I. Pigment Yellow 74 and the at least one monoazo pigment of the formula (1).

9) (Canceled)

10) (Previously Presented) The colorant as claimed in claim 1, wherein the pigment composition is substantially free from alkali-soluble resins.

11) ((Previously Presented)) An ink-jet ink or a color filter pigmented with the colorant according to claim 1.

12) ((Previously Presented)) A method of coloring an ink-jet ink or a color filter comprising the step of adding to the ink-jet ink or color filter a pigment composition comprising between 88.0 and 99.9 overall mol% of C.I. Pigment Yellow 74 molecules and between 14.0 and 0.1 overall mol% of at least one monoazo pigment of the formula (1)



wherein R' is Cl, OCH₃, CH₃ or NO₂.